

Combi Primer

Product properties

White-pigmented primer that produces a matt surface. Produces a uniform surface prior to additional treatment. Used before painting or installing wallpaper and wall coverings.

- **Primer agent**
- **Pigmented**
- **Matt**



Product use

Plaster, concrete, cardboard-coated gypsum board and filled surfaces before hanging wallpaper or as pigmented primer before painting with ceiling and wall paint.
Also used as a discolourer for priming and detecting pores in concrete.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning and sanding.
Remove dirt, grime, grease and chalking materials by cleaning with Fluren 37.
Water-soluble discolouration, nicotine and soot can be cleaned with Fluren 49.
Sand surface to matt finish as required.
Cracks, unevenness and holes must be filled.

Application

Brush or roller.
Decide your choice of tool/utensil depending on the finish.
Apply wet on wet and finish by brushing/rolling in the same direction.
Cold/heat can affect the viscosity of the material.
Condensation during drying/curing must not occur.
Cold and increased humidity extends drying time, full curing and recoat interval.
Increased temperature and low atmospheric humidity reduce drying time and full curing.
Always perform a test treatment for a check and acceptance of adhesion and result.

Expected result

Matt, covered surface.
Finish with wall covering and/or paint in desired gloss and colour.

Please note!

On a chalking substrate and on a gypsum-based filler such as Flügger Filler or Repa Quick, the necessary penetration and adhesion is not achieved with Flügger Combi Primer.
In this case, Flügger Sealer Non-drop is recommended as a primer.

Environmental information

Minimize your paint waste by pre-estimating how much paint you need.

Remove as much paint as possible from tools before cleaning.

Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.

Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.

Store excess paint correctly so that leftovers can be used and environmental impact is minimised.

Storage

Cool, frost-free, and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.

Avoid inhalation of spray mist and grinding dust.

Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Product Type	Priming paint
Density (kgs/l)	1.30
Solids Weight %	44
Solids Vol. %	28
Nominal spreading rate (m ² /ltr.)	6
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	1
Recoatable at 20° C, 60 % RH (Hours)	3
Fully cured at 20° C, 60 % RH (Days)	28
Dilution	Do not dilute
Cleaning of Tools etc.	Water

Current TDS Version

October 2024

Replaces TDS Version

May 2024