

Natural Wood Cleaner

Product properties

Cleaning agent for untreated, lye-treated, soap-treated, oiled or varnished surfaces before new treatment and maintenance.

- Removes grease, soap, wax and dirt
- Prepare the surface effectively before treatment
- For use in interiors



Labelling



Product use

Cleaning of untreated, lye-treated, soap-treated, oiled or varnished surfaces such as furniture, countertops and floors. For all types of wood before treatment with lye, soap, oil or varnish.

Substrate

Must be clean, dry, firm and suitable for surface treatment.
The surface must be able to withstand water and alkalines, pH 10.5.

Treatment

Mix 1 part Flügger Natural Wood Cleaner with 20 parts warm water, for varnished surfaces 1 part to 40 parts water. Wash the surface and let the mixture work for 5 minutes before wiping off with clean water. Repeat the treatment if the surface is extremely dirty. The surface must be completely dry before subsequent treatment.

Application

Mop, floor scrub or cloth.
Always wash along the length of the wood.
Do not leave the surface wet.
Treat cleaned surfaces with lye, soap, oil or varnish.

Expected result

Uniformly cleaned surface free of grease, soap, wax and dirt.

Please note!

Flügger Natural Wood Cleaner can etch glass and attack metals.
So make sure to cover surroundings to protect against splashing.

Environmental information

Remove the cap before sorting the packaging for recycling.

Storage

Cool, frost free and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.

Technical Data

Product Type	Cleaning
Density (kgs/l)	1.04
pH	10.5
Mixing ratio	Varnished wood floor: 1 part to 40 parts water Oiled wood floor: 1 part to 20 parts water Untreated or soap-treated wood floor: 1 part to 20 parts water
Contains	AQUA, Poly(oxy-1,2-ethanediyl), α-(2-propylheptyl)-ω-hydroxy-, Quaternary ammonium compounds, (hydroxyethyl)dimethyl, ethoxylated, chlorides, C9-11 PARETH-6, TRISODIUM DICARBOXYMETHYL CITRIC ACID, XANTHAN GUM.
Nominal spreading rate (m²/ltr.)	250
Long spreading rate (m²/l.)	300
Short Spreading rate (m²/ltr.)	200
Min. working temp. during application and drying/curing	Min. +15°C
Humidity	Max. humidity 80 % RH.
Recoatable at 20° C, 60 % RH (Hours)	8
Dilution	Water
Cleaning of Tools etc.	Water
Country of Origin	Denmark

Current TDS Version

December 2024

Replaces TDS Version

April 2024