Sandplast LW

Product properties

Filler for rooms exposed to varying moisture conditions. Contains light, fine-grained filler paste with good filling capacity. Finish by treating with a wall covering and/or suitable ceiling or wall paint in the desired colour and gloss.



- Moisture-stable filler
- · High tensile strength
- Blue-toned

Labelling





Product use

Filling and reinforcing of joints with Marco Spark-Perf or Sheetrock plaster tape and filling screw holes on gypsum plasterboard. Patching and filling when smoothing out plaster, concrete, lightweight concrete, gypsum plasterboard and previously painted surfaces.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning, sanding and dusting. Remove dirt, grime, grease and chalking materials by cleaning with Fluren 37. Water-soluble discolouration, nicotine and soot can be cleaned with Fluren 49. Sand flat hard, slippery surfaces. Apply the filler paste and smooth out. Dust off and fill the gypsum board joints and place the plaster tape with the prefabricated fold against the joint, pressing firmly with the knife and pressing down into the wet filler paste. Press the tape in so far that a thin layer of filler paste is deposited on the outside of the tape. At the same time, scrape the filler over the tape. Once it has dried, fill the joints and screw holes twice. Sand the surface and prime it before any additional treatment.

Application

Apply and smooth out using a filler knife. Decide your choice of tools based on the size of the surface. Apply a sufficient amount and then work and smooth out the filler paste. Cold/ heat can affect the viscosity of the material. Condensation during drying/curing must not form. Cold and increased humidity extends drying time, full curing and recoating interval. Increased temperature and low atmospheric humidity reduce drying time and full curing. Risk of shrinkage where the filler paste is not completely cured before additional treatment. Always perform a test treatment for a check and acceptance of adhesion and result.

Expected result

Even surface for additional treatment.

Please note!

Install the gypsum board according to the manufacturer's instructions and standards. See the Flügger user directions for gypsum board, filling of joints.

Environmental information

Clean off the paint from tools and wash them with water. Bring remains of fluent paint to the local recycling centre. Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

Storage

Cool, frost-free, and tightly closed

Supplementary Info

The product meets the requirements of M1: Emission Classification of Building Materials: Protocol for Chemical and Sensory Testing of Building Materials.

For this product there is issued an: **Environmental Product Declaration**

Technical Data

Color (plaster) Density (kgs/l) Solids Weight % Solids Vol. % Nominal spreading rate (m²/ltr.) Min. working temp. during application and drying/curing Min. +10°C Humidity Max. humidity 80 % RH. Drying time at 20° C, 60 % RH (Hours) 2 Recoatable at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) Blue-toned Blue-toned Blue-toned 0.99 0.99 58 68 56 Max. humidity 80 % RH. 2 68 68 68 68 68 68 68 68 68		
Density (kgs/l) Solids Weight % Solids Vol. % 56 Nominal spreading rate (m²/ltr.) Min. working temp. during application and drying/curing Min. +10°C Humidity Max. humidity 80 % RH. Drying time at 20° C, 60 % RH (Hours) 2 Recoatable at 20° C, 60 % RH (Hours) 20 Fully cured at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm)	Product Type	Plaster & Sealant
Solids Weight % Solids Vol. % 56 Nominal spreading rate (m²/ltr.) 1 Min. working temp. during application and drying/curing Min. +10°C Humidity Max. humidity 80 % RH. Drying time at 20° C, 60 % RH (Hours) 2 Recoatable at 20° C, 60 % RH (Hours) 20 Fully cured at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) 58 58 58 58 58 60 60 60 60 60 70 70 70 70 70	Color (plaster)	Blue-toned
Solids Vol. % 56 Nominal spreading rate (m²/ltr.) Min. working temp. during application and drying/curing Min. +10°C Humidity Max. humidity 80 % RH. Drying time at 20° C, 60 % RH (Hours) 2 Recoatable at 20° C, 60 % RH (Hours) 20 Fully cured at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) 0.2	Density (kgs/l)	0.99
Nominal spreading rate (m²/ltr.) Min. working temp. during application and drying/curing Min. +10°C Humidity Max. humidity 80 % RH. Drying time at 20° C, 60 % RH (Hours) 2 Recoatable at 20° C, 60 % RH (Hours) 20 Fully cured at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) 1	Solids Weight %	58
Min. working temp. during application and drying/curing Min. +10°C Humidity Max. humidity 80 % RH. Drying time at 20° C, 60 % RH (Hours) 2 Recoatable at 20° C, 60 % RH (Hours) 20 Fully cured at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) 0.2	Solids Vol. %	56
Humidity Max. humidity 80 % RH. Drying time at 20° C, 60 % RH (Hours) 2 Recoatable at 20° C, 60 % RH (Hours) Fully cured at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) Max. humidity 80 % RH. 2 0 0 0 0 0 0 0 0 0 0 0 0	Nominal spreading rate (m²/ltr.)	1
Drying time at 20° C, 60 % RH (Hours) Recoatable at 20° C, 60 % RH (Hours) 20 Fully cured at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) 2 2 2 2 2 2 2 2 2 2 2 2 2	Min. working temp. during application and drying/curing	Min. +10°C
Recoatable at 20° C, 60 % RH (Hours) 20 Fully cured at 20° C, 60 % RH (Days) 28 Adhesion on concrete (MPa) 0.86 Layer thickness (nominal mm) 2 Grain size (max. Mm) 0.2	Humidity	Max. humidity 80 % RH.
Fully cured at 20° C, 60 % RH (Days) Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) 0.2	Drying time at 20° C, 60 % RH (Hours)	2
Adhesion on concrete (MPa) Layer thickness (nominal mm) 2 Grain size (max. Mm) 0.86 2	Recoatable at 20° C, 60 % RH (Hours)	20
Layer thickness (nominal mm) 2 Grain size (max. Mm) 0.2	Fully cured at 20° C, 60 % RH (Days)	28
Grain size (max. Mm) 0.2	Adhesion on concrete (MPa)	0.86
	Layer thickness (nominal mm)	2
Cleaning of Tools etc. Water	Grain size (max. Mm)	0.2
	Cleaning of Tools etc.	Water

Current TDS Version

December 2024

Replaces TDS Version

March 2024